



# Light Burned Technical Grade Magnesium Oxide

<b>DESCRIPTION</b>	MagChem® 40 is a high purity technical grade of magnesium oxide processed from magnesium-rich brine. This fine white powder has a very high reactivity index and a low bulk density.		
<b>USES</b>	MagChem 40 is well suited for many rubber formulations, particularly neoprene. It finds wide use as a filler, anti-caking agent, and pigment extender. MagChem 40 is extremely efficient in chemical processes where ease of conversion is a factor. It is also used in the production of oil additives and the desilication of water.		
<b>COMPOSITION</b>		<b>Typical</b>	<b>Specifications</b>
	Magnesium Oxide (MgO), % ignited basis	98.2	97.0 min.
	Calcium Oxide (CaO), %	0.8	1.0 max.
	Silicon Oxide (SiO <sub>2</sub> ), %	0.35	0.5 max.
	Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ), %	0.15	0.3 max.
	Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ), %	0.10	0.2 max.
	Chloride (Cl), %	0.30	0.5 max.
	Sulfate (SO <sub>3</sub> ), %	0.05	0.3 max.
	Loss on Ignition, %	2.3	3.0 max.
<b>PHYSICAL PROPERTIES</b>	Bulk Density, loose, lb/ft <sup>3</sup> (g/cm <sup>3</sup> )	22 (0.35)	
	Mean Particle Size, microns	3 - 8	
	Surface Area, m <sup>2</sup> /g	45	
	Activity Index, seconds	9	7 - 11
	Screen Size, % passing 325 mesh, wet	99.5	99.0 min.
<b>PACKAGING</b>	Available in bulk carload and truckload, 50-lb polyethylene-lined, multi-walled bags and 1000-2000-lb and 1000-kg bulk sacks.		
<b>STORAGE</b>	Store in dry place. Exposure to moisture may cause caking.		

#### NOTICE

THE INFORMATION CONTAINED HEREIN IS, TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE, ANY RECOMMENDATIONS OR SUGGESTIONS MADE ARE WITHOUT WARRANTY OR GUARANTEE OF RESULTS SINCE CONDITIONS OF HANDLING AND OF USE ARE BEYOND OUR CONTROL; WE, THEREFORE, ASSUME NO LIABILITY FOR LOSS OR DAMAGE INCURRED BY FOLLOWING THESE SUGGESTIONS. SELLER WARRANTS ONLY THAT THIS PRODUCT WILL MEET THE SPECIFICATIONS SET FORTH. ANY OTHER REPRESENTATION OR WARRANTY, EITHER EXPRESS OR IMPLIED IS SPECIFICALLY DISCLAIMED INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY. SELLER'S AND MANUFACTURER'S ONLY OBLIGATION SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT PROVED TO BE DEFECTIVE. BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR USER'S INTENDED APPLICATION AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE IN TORT, CONTRACT OR UNDER ANY THEORY FOR ANY LOSS OR DAMAGE, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR THE INABILITY TO USE THE PRODUCT.

#### Martin Marietta Magnesia Specialties Inc.

P.O. Box 15470  
Baltimore, MD USA 21220-0470  
Phone: 800 648-7400  
Or: 410-780-5500  
FAX: 410-780-5777  
www.magspecialties.com

#### Martin Marietta Magnesia Specialties



MagChem is a trademark of  
Martin Marietta Magnesia Specialties Inc.

Copyright ©2000 by Martin Marietta Magnesia Specialties Inc.